

• TRUSTED QUALITY SINCE 1921 •



ELASTOMERIC ROOF PATCH

DESCRIPTION AND USES

Rust-Oleum® Elastomeric Roof Patch is a white, acrylic elastomeric roof sealant intended for application to metal, asphalt, modified bitumen and most single-ply roofs. The highly flexible, rubber-like elasticity accommodates wide swings in temperature and significant building movement. Rust-Oleum Elastomeric Roof Patch is UV stable and may be used to repair roofs and seal metal roof fasteners.

For exterior use only.

PRODUCT FEATURES

- Excellent adhesion & flexibility
- Patches seams & splits and seals roof fasteners
- Easy water clean up
- 10 Year warranty
- Use for residential shingled, modified bitumen, built-up, metal, and aged single-ply roofing systems

PRODUCT

SKU	DESCRIPTION
301898	1 Gallon

COMPANION PRODUCTS

SKU	DESCRIPTION
364544	130 Urethane Acrylic Roof Primer - 4.75 Gallons
365241	130 Urethane Acrylic Roof Primer - 55 Gallons
365242	130 Urethane Acrylic Roof Primer - 275 Gallons
355905	115 Hybrid Epoxy 1K (Gray) - 4.75 Gallons
326036	105 Single-Ply Adhesion Primer – 4.75 Gallons
361456	One Step Roof Prep – 1 Gallon
361455	One Step Roof Prep – 5 Gallons

PRODUCT APPLICATION

SURFACE PREPARATION

All surfaces must be clean and free from dirt, grease, oil, mold, algae, loose granules, loose paint, rust, excess chalk and other foreign matter which could prevent proper adhesion. Use a high-pressure wash of at least 2,000 psi. Clean with Rust-Oleum One Step Roof Prep, or other suitable cleaner to remove all grease or oily deposits. Surface temperatures should be under 100°F (38°C) to avoid premature curing. If the roof surface is hot, apply a light water spray to reduce the surface temperature.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-Approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

BUR/MODIFIED BITUMEN: Must be primed with Rust-Oleum 130 Urethane Acrylic Roof Primer*.

METAL: Bare galvanized metal does not require a primer if there is no rust present. Surface must be clean and dry. Steel surfaces must be primed, as does rusty or corroded metal. If the metal panel is not Kynar or previously coated, the surface must be cleaned of all rust as thoroughly as possible by wire brush, power tools or power washed. The surface must be primed with Rust-Oleum 115 Hybrid Epoxy Primer*. Adhesion test may be required. Consult with your Rust-Oleum representative.

EPDM, PVC, TPO AND HYPALON: Must be primed with Rust-Oleum 105 Single-Ply Adhesion Primer*.

* See primer labels and technical data sheet for correct surface preparation and application procedures.

APPLICATION

Apply only when air, material, and surface temperatures are between 40-100°F (4-38°C) and the relative humidity is below 85%.

Apply with a brush or trowel (1/8-1/4") thick. Extend the material two inches on either side when sealing fasteners. For added strength, reinforce seams and repairs with Rust-Oleum Universal Patching Fabric between two applications of Rust-Oleum Elastomeric Roof Patch.

COVERAGE

Approximately 12 square feet per gallon when applied at 1/8 inch (125 mils) wet film thickness. Actual coverage may vary depending upon application method.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow to dry at least 4 to 8 hours for a thorough dry before recoating with an acrylic based roof coating. Product will reach full cure in 24 hours. Environmental or site specific conditions may lead to a variation in dry time.

CLEAN-UP

Wash tools and equipment with soap and water. Wipe up spills before they dry. Properly dispose of all soiled rags and containers.

LIMITATIONS

Do not store above 90°F (32°C). Apply only at temperatures above 40°F (4°C) and when the surface temperature is under 100°F (38°C). Do not apply if rain is expected within 48 hours of application or if the humidity is greater than 90%.

PROTECT FROM FREEZING

	TECHNICAL DATA	ROC-94
• TRUSTED QUALITY SINCE 1921 • 	ELASTOMERIC ROOF PATCH	

PHYSICAL PROPERTIES

		ELASTOMERIC ROOF PATCH
Resin Type		Elastomeric Acrylic
Pigment Type		Titanium Dioxide, Mineral
Solvents		Water
Weight	Per Gallon	11.5 lbs.
	Per Liter	1.38 kg
Solids	By Weight	69%
	By Volume	55%
VOC		<25 g/l
Practical Coverage		Approximately 12 square feet per gallon when applied at 1/8 inch (125 mils) wet film thickness
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Through Dry	4-8 hours
	Full Cure	24 hours depending on temperatures
Shelf Life		3 years
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.