

• TRUSTED QUALITY SINCE 1921 •



RUST-OLEUM® EXTREME WET OR DRY ROOF REPAIR

DESCRIPTION AND USES

Rust-Oleum® Extreme Wet or Dry Roof Repair is a premium quality, heavily fibered, asphalt-based roof cement blended with penetrating oils and plasticizing agents that can be applied directly to cold, hot, wet, dry or underwater surfaces. Extreme Wet or Dry Roof Repair can be used to repair and restore flashings and roofing defects such as blisters, cracks and punctures. It can also be used to bond new asphalt ply and modified bitumen membrane flashings or seal vents, shingles, skylights and chimneys. Extreme Wet or Dry Roof Repair resists sags and spreads easily in cold conditions.

For exterior use only.

PRODUCT FEATURES

- Stops leaks in wet or dry conditions
- Rubberized for increased strength
- Heavily fibered for long lasting repairs
- 20 Year warranty
- Use for: residential shingled, modified bitumen, and built-up roofing systems

PRODUCTS

SKU	DESCRIPTION (Black)
351249	10.1 fl. oz.
351237	1 Gallon
351250	2.75 Gallons

PRODUCT APPLICATION

SURFACE PREPARATION

All surfaces must be clean, sound and free from dirt, grease, oil, mold, algae, loose granules, loose gravel, loose paint, rust, excess chalk and other foreign matter which could prevent proper adhesion.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN YOUNG CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply only when air, material, and surface temperatures are between 40-120°F (4-49°C).

Apply with a trowel directly over a cleaned substrate at a rate of 12 square feet per gallon or approximately 1/8" thick. When making roof repairs or striping over the top of flashing laps, perform a 3-course repair consisting of one application of Extreme Wet or Dry Roof Repair followed by an embedded strip of **Rust-Oleum Universal Patching Fabric** or other mesh, followed by a final application of Extreme Wet or Dry Roof Repair.

COVERAGE

Each gallon will cover approximately 12 square feet when applied at 1/8" thick. Actual coverage will vary depending upon ambient temperature and surface conditions.

CARTRIDGE APPLICATION

Apply only when air, material, and surface temperatures are between 0-100°F (-18-38°C). For application in cold weather (under 40°F), store unopened container in a warm room for 24 hours prior to use.

Place cartridge in a cradle type caulking gun. Cut tip and puncture seal in spout. Squeeze trigger slowly. Apply 1/4-1/2" bead of sealant to areas that are to be sealed.

CARTRIDGE COVERAGE

Will cover approximately 25 linear feet. Actual coverage will vary depending upon application method.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Product will reach full cure in 24 hours.

Environmental or site specific conditions may lead to a variation in dry time.

CLEAN-UP

Wash tools and equipment with mineral spirits. Wipe up spills before they dry. Properly dispose of all soiled rags and containers.

LIMITATIONS

Not for use on coal tar membranes. Repairs made to wet surfaces should be considered temporary as trapped moisture may expand when heated by the sun causing blisters and potentially new leaks. For permanent repairs, open up the area and allow it to dry thoroughly.

	TECHNICAL DATA	ROC-160
• TRUSTED QUALITY SINCE 1921 • 	RUST-OLEUM® EXTREME WET OR DRY ROOF REPAIR	

PHYSICAL PROPERTIES

		EXTREME WET OR DRY ROOF REPAIR
Resin Type		Asphalt
Pigment Type		Mineral
Solvents		Mineral Spirits
Weight	Per Gallon	8.5 lbs.
	Per Liter	1.02 kg
Solids	By Weight	77%
	By Volume	73%
Volatile Organic Compounds		Max 250 g/l
Recommended Dry Film Thickness (DFT) Per Coat		90 mils (3/32")
Wet Film Thickness to achieve DFT (unthinned material)		125 mils (1/8")
Practical Coverage at Recommended DFT (assume 15% material loss)		Approximately 12 square feet depending on ambient temperature and surface conditions.
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Through Dry	2-4 hours
	Full Cure	24 hours
Shelf Life		3 years
Flash Point		105°F (41.5°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.